
















# TECHNICAL SPECIFICATIONS

	PHYSICAL & CHEMICAL	NORM / TEST METHOD	FUORIFORMATO
	SIZE	ISO 10545-2	MAX DEVIATION ON THE SIDE +/- 0.5 mm
	SIZE	ISO 10545-2	MAX DEVIATION ON THE DIAGONAL +/- 1.0 mm
	WEIGHT (FOR 5-6MM THICKNESS)	FUORIFORMATO	AVERAGE VALUE 14 KG / mq
	WATER ABSORPTION	ISO 10545-3	AVERAGE VALUE 0.1 % ( < 0.3% )
	BREAKING LOAD IN N / SAMPLES 200 X 300 mm	ISO 10545-4	AVERAGE VALUE 1100
	BENDING STRENGTH IN N / mm <sup>2</sup>	ISO 10545-4	AVERAGE VALUE 50 (SAMPLE DIMENSIONS 200 X 300 mm)
	MOHS SCALE HARDNESS	UNI EN 101	CLASS FROM 4 to 7
	RESISTANCE TO DEEP ABRASION	ISO 10545-7	PEI DA 3 A 5
	COEFFICIENT OF LINEAR THERMAL EXPANSION LINEARE / 10 <sup>-6</sup> / °C	ISO 10545-8	6.6
	RESISTANCE TO THERMAL SHOCK	ISO 10545-9	RESISTANT
	CHEMICAL RESISTANCE	ISO 10545-13	CLASS FROM A to C
	STAIN RESISTANCE	ISO 10545-14	CLASS FROM 4 to 5
	FROST RESISTANCE	ISO 10545-12	RESISTANT
	FIRE REACTION	EN13501 (REV. 2005)	A1 (DECISION96/603/CE AS AMENDED)
	SKID RESISTANCE (FLOOR 1000X1000)	DIN51130	R9